



Ceramic Matrix

APPLICATIONS

INTERIOR WALLS	EXTERIORS	POOLS	SHOWERS	LIGHT DUTY FLOORS & COUNTERTOPS
YES	NO	NO	YES	YES (matte white only)

Recommended applications must follow detailed installation and usage instructions

PURE WHITE/NATURAL ASTM RESULTS

TEST #	TYPE OF TEST	RESULTS
Test #C650	Chemical Resistance	No affect, 24 hour duration
Test #C1027	Abrasion Resistance	Class 2, Residential
Test #C1378	Stain Resistance	No affect, 24 hour duration

PURE MATTE WHITE ASTM RESULTS

TEST #	TYPE OF TEST	RESULTS
Test #C650	Chemical Resistance	No affect, 24 hour duration
Test #C1027	Abrasion Resistance	Class 4, Commercial
Test ANSI A137.1	Wet Dynamic Coefficient of Friction	DCOF Average .42
Mohs' Scratch Hardness	Scratch Hardness	Mohs 7 (Quartz)