








Stonehenge

Dry - Pressed Ceramic Tiles


ISO 13006 Annex G - UNI EN 14411 Annex G - Bla UGL

ANSI 137.1 CBR

TECHNICAL FEATURES CARATTERISTICHE TECNICHE	STANDARD NORMA	VALUE VALORI
 WATER ABSORPTION (AVERAGE VALUE EXPRESSED IN %) ASSORBIMENTO D'ACQUA (VALORE MEDIO IN %)	UNI EN ISO 10545/3 ASTM C373	CONFORME COMPLIANT
 MODULUS OF RUPTURE RESISTENZA ALLA FLESSIONE	UNI EN ISO 10545/4	≥ 45 N/mm ²
 BREAKING STRENGTH FORZA DI ROTTURA	UNI EN ISO 10545/4 ASTM C648	≥ 2000 N 400 Lbs
 FROST RESISTANCE RESISTENZA AL GELO	UNI EN ISO 10545/12 ASTM C1026	CONFORME UNAFFECTED
 CHEMICAL RESISTANCE TO HIGH AND LOW ACID AND BASIC CONCENTRATIONS RESISTENZA CHIMICA AD ALTE E BASSE CONCENTRAZIONI DI ACIDI E BASI	UNI EN ISO 10545/13 ASTM C-650	A - LA - HA UNAFFECTED
 STAIN RESISTANCE RESISTENZA ALLE MACCHIE	UNI EN ISO 10545/14	5
 SLIP RESISTANCE COEFFICIENTE DI ATTRITO		NAT. DIN EN 16165 Annex B R10 DIN EN 16165 Annex A B (A+B) ANSI A326.3:2017 DCOF WET ≥ 0,50



Heavy pedestrian traffic (e.g. railway stations, airports, retail malls).



PACKING AND WEIGHT IMBALLAGGI E PESI

Size Formato Inch	Thickness Spessore mm	Pieces x Box Pz. x Scat.	Sq. F. x Box Piedi Q. x Scat.	Weight x Box Peso x Scat. Lbs	Boxes x Pal. Scat. x Pal.	Sq. F. x Pal. Piedi Q. x Pal.	Weight x Pal. Peso x Pal. Lbs
23 ^{5/8} x 47 ^{1/4} 60x120 Naturale	9.5	2	15.26	64.14	30	457.8	1924.20
11 ^{13/16} x 23 ^{5/8} 30x60 Naturale - Line	8.5	9	17.01	64.89	32	544.32	2076.48
11 ^{13/16} x 11 ^{13/16} 30x30 Mosaico Naturale	8.5	10	9.69	32.43	54	523.13	1751.22
2 ^{3/4} x 23 ^{5/8} 7x60 Bullnose Nat.	8.5	15	-	27.00	48	-	1296.00