









4.5 mm / GLASS

		Test method	Reference value	Declared value
	Barefoot slip resistance	DIN-EN-16165-ANNEX-A	-	Cl. C
	Amount of water absorbed, in percentage	ISO-10545-3	-	< 0,5%
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	-	< 300 mm ³
	Glaze crazing resistance	ISO-10545-11	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to high concentrations of acids and alkali	ISO-10545-13	-	UHA - GHA
	Resistance to low concentrations of acids and alkali	ISO-10545-13	-	ULA - GLA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	-	UA - GA
	Resistance to staining	ISO-10545-14	-	Cl. 5

Note:

Slipperiness test results are referred exclusively to mosaic.